

BINDAKOTE

THE FOLLOWING DATA REFERS TO BINDAKOTE ICE WHITE RECYCLED 50%

	Method		+/-	280 g/m ²	350 g/m ²	450 g/m ²
Basis weight	ISO 536	g/m ²	5%	280	350	450
Caliper	ISO 534	µm	5%	300	385	495
Bulk	ISO 534	cm ³ /g	-	1,1	1,1	1,1
Gloss 20°	ISO 2813	%	>	45	45	45
ISO Brightness	ISO 2470	%	2	84	84	84
CIE Whiteness	ISO 11475	%	7	111	111	111
Moisture Content	ISO 287	%	1	5,5	5,5	5,5
L&W Stiffness MD (15°/50mm)	ISO 2493	mN	>	140	230	480
L&W Stiffness CD (15°/50mm)	ISO 2493	mN	>	40	115	240

THE FOLLOWING DATA REFERS TO BINDAKOTE COLOURS

	Method		+/-	250 g/m ²
Basis weight	ISO 536	g/m ²	5%	250
Caliper	ISO 534	µm	5%	293
Bulk	ISO 534	cm ³ /g	-	1,2
Moisture Content	ISO 287	%	1	5
L&W Stiffness MD (15°/50mm)	ISO 2493	mN	>	140
L&W Stiffness CD (15°/50mm)	ISO 2493	mN	>	70

THE FOLLOWING DATA REFERS TO BINDAKOTE BLUE ON BLACK

	Method		+/-	250 g/m ²
Basis weight	ISO 536	g/m ²	5%	250
Caliper	ISO 534	µm	5%	293
Bulk	ISO 534	cm ³ /g	-	1,2
Moisture Content	ISO 287	%	1	5
L&W Stiffness MD (15°/50mm)	ISO 2493	mN	>	140
L&W Stiffness CD (15°/50mm)	ISO 2493	mN	>	70

THE FOLLOWING DATA REFERS TO BINDAKOTE BLACK ON BLACK

	Method		+/-	115 g/m ²	250 g/m ²	350 g/m ²
Basis weight	ISO 536	g/m ²	5%	115	250	350
Caliper	ISO 534	µm	5%	120	293	420
Bulk	ISO 534	cm ³ /g	-	1,1	1,2	1,2
Moisture Content	ISO 287	%	1	5	5	5
L&W Stiffness MD (15°/50mm)	ISO 2493	mN	>	210	140	400
L&W Stiffness CD (15°/50mm)	ISO 2493	mN	>	105,0	70	200

Special makings are available upon request.

