



**TESLIN®**  
Enabling Substrate Technology from PPG

## Teslin® Substrate Technical Data

*Teslin*® substrate, from PPG Industries, is a microporous, dimensionally stable, highly filled, single-layer, polyolefin synthetic material. A non-abrasive inorganic filler comprises 60 percent of the weight, and it is 65 percent air by volume. The porous, uncoated nature of *Teslin* substrate allows inks, adhesives, coatings, and laminating films to penetrate into its structure, forming strong interlocking bonds with the substrate.

### Typical Properties<sup>1</sup>

	SP 600	SP 700 <sup>2</sup>	SP 800 <sup>2</sup>	SP 1000 <sup>2</sup>	SPID 1000	SP 1000 Blue	IJ 1000 WP	Digital 1000	SP 1200 <sup>2</sup>	SP 1400 <sup>2</sup>	SPID 1400	HD 1400	SP 1800	Reference
Gauge (mils)	5.7	7.0	8.0	10.0	10.0	10.0	10.0	10.5	12.0	14.0	14.0	14.0	18.0	ASTM D-374
Tolerance (+/- mils)	0.5	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.8	0.9	0.9	0.9	1.2	
Gauge (microns)	145	178	203	254	254	254	254	267	305	356	356	356	457	
Tolerance (+/- microns)	13.0	17.8	17.8	17.8	17.8	17.8	17.8	17.8	20.3	22.9	22.9	22.9	30.5	
Yield (si/lb)	7,288	6,102	5,242	4,210	4,210	4,210	4,210	3,847	3,414	2,888	2,888	2,426	1,909	ASTM D-3776
Grammage (g/m <sup>2</sup> )	97	115	134	167	167	167	167	183	206	243	243	290	368	
Basis Weight (oz/sq yd)	2.85	3.40	3.96	4.93	4.93	4.93	4.93	5.39	6.07	7.18	7.18	8.55	10.86	
(lbs/500 sq yd)	65	77	90	108	108	108	n/a	123	138	163	163	195	249	
Master Roll Configuration														
Mill Roll Length (ft)	7,000	6,000	5,250	5,000	5,000	5,000	n/a	5,000	3,750	3,300	3,300	3,300	2,400	
Mill Roll Length (m)	2,134	1,829	1,601	1,524	1,524	1,524	n/a	1,524	1,143	1,006	1,006	1,006	732	
Roll Weight (lbs)	657	673	685	812	812	812	n/a	812	751	781	781	930	860	
Roll Weight (kg)	298	305	311	368	368	368	n/a	368	341	354	354	422	390	
Tensile Properties														
MD Tensile Strength														
lb/fin	11.1	13.3	15.4	18.3	18.3	18.3	18.3	21.8	19.9	22.6	22.6	26.6	25.0	
N/cm	19.4	23.3	27.0	32.0	32.0	32.0	32.0	38.2	34.8	39.6	39.6	46.6	44.0	ASTM D-882
CD Tensile Strength														
lb/fin	5.3	6.3	7.3	8.6	8.6	8.6	8.6	10.6	9.7	11.2	11.2	12.1	12.0	
N/cm	9.3	11.0	12.8	15.1	15.1	15.1	15.1	18.6	17.0	19.6	19.6	21.2	21.0	
Elmendorf Tear (g)														
MD	77	100	135	198	198	198	198	274	239	292	292	311	416	ASTM D-1922
CD	tore to MD	tore to MD	tore to MD	tore to MD	tore to MD	tore to MD	tore to MD	tore to MD	tore to MD	tore to MD	tore to MD	tore to MD	tore to MD	
Brittleness Temperature	<-70°C	<-70°C	<-70°C	<-70°C	<-70°C	<-70°C	<-70°C	<-70°C	<-70°C	<-70°C	<-70°C	<-70°C	<-70°C	ASTM D-746
Optical Properties														
Brightness %	89	89	90	91	91	91	92	91	92	92	92	92	92	ISO-2470
Whiteness Index	80	80	80	80	80	95	80	88	83	85	85	82	80	ASTM E-313
Opacity (%)	90	92	94	96	96	96	96	95	98	98	98	99	99	ISO-2471
Transmission (%)	17	15	11	8	8	8	8	9	6	5	5	4	3	ASTM D-1003
Sheffield Smoothness														
Top	46	28	32	27	27	27	45	29	29	29	29	49	63	ASTM T-538
Bottom	74	70	74	56	56	56	73	52	52	52	52	99	97	

<sup>1</sup> Specifications are based on English units of measurement. Metric values are provided for convenience and are not to be considered precise values. Standard master roll width is 57"/1447mm and 28"/711mm OD. 40"/1016mm OD rolls available upon request.

<sup>2</sup> The maximum allowable shrinkage for TS grade is 2% (measured at 135 °C for 15 minutes in a forced air oven). All other properties/specifications are the same for TS and SP grades. Custom widths up to 60"/1549mm available upon request. Digital 1000 is available in 12.5"/320mm and 20"/500mm width x 1400'/427m length rolls. Master rolls are put up on 6"/152mm ID cores.



**PPG Industries**

PPG Industries • 440 College Park Drive • Monroeville, PA 15146  
800.437.8318 • +1.724.325.5924 • [www.teslin.com](http://www.teslin.com)

The information contained herein represents the best efforts of PPG Industries, Inc. in compiling this information. Data was drawn from lab tests performed by PPG and by independent testing laboratories. Nevertheless, there are no guarantees, implied or otherwise, that this information is complete and error-free. PPG Industries, Inc. disclaims all warranties of any kind, either expressed or implied, including, but not limited to, all warranties of merchantability and fitness for a particular purpose. PPG Industries, Inc. shall not be liable for any damages whatsoever resulting from the use of the product, including, without limiting the generality of the foregoing, for any special, incidental, indirect, or consequential damages or for the loss of profit or revenue, even if PPG Industries, Inc. has been advised of the possibility of such loss or damage.