

Chantaffiche™ 250

Affichenpapier mit blauer Rückseite für den Offsetdruck |

Affiche paper with blue back side for offset printing

Technisches Datenblatt | Technical data sheet

Flächenbezogene Masse:
Grammage: 115 g/m²

Ident-Nr.: 711296

Version: 01/2022

	Eigenschaft Characteristic	Methode Method	Einheit Unit	Typischer Wert Typical value	Toleranz Tolerance
1	Flächenbezogene Masse Grammage	DIN EN ISO 536	g/m ²	115	± 5
2	Dicke Thickness	DIN EN ISO 534	µm	150	± 10
3	CIE Weißgrad CIE Whiteness	ISO 11475	%	104	± 5
4	Opazität trocken Dry opacity	ISO 2471	%	99	± 1
5	Opazität nass Wet opacity	ISO 2471	%	98	± 2
6	Wasseraufnahme Cobb 60" RS Water absorption Cobb 60" bs	DIN EN ISO 535	g/m ²	25	± 5
7	Nassbruchkraft längs Wet tensile strength md	DIN ISO 3781	kN/m	> 0.8	
8	Nassbruchkraft quer Wet tensile strength cd	DIN ISO 3781	kN/m	> 0.7	
9	Nassdehnung quer Wet expansion	DIN 54517	%	2.2	± 0.5

Kontakt / Contact:

KÄMMERER Paper GmbH

Römereschstraße 33

Phone +49 541 604-385

Elke.tilch@kaemmerer-paper.com

D-49090 Osnabrück

www.kaemmerer-paper.com

DISCLAIMER: The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed, including without limitation any warranty of merchantability and fitness for use. All users of the material are responsible for assuring that it is suitable for their needs, environment and end use. All data is subject to change as KÄMMERER Paper GmbH deems appropriate. Refer to www.kaemmerer-paper.com for contact information.