


BUCHBINDERPAPPE

Haupt Spezial C

BB-BOARD HAUPT SPECIAL C
CARTÓN HAUPT SPECIAL C
CARTON HAUPT SPÉCIAL C



TECHNISCHE WERTE | TECHNICAL FIGURES

DICKE / Thickness (mm)	Flächengewicht Substance (g/m ²)	Biegesteifigkeit längs Bending Stiffness longitudinal (mNm)	Biegesteifigkeit quer Bending Stiffness transverse (mNm)	Berstdruck Burst pressure (kPa)
1,0	700	380	160	750
1,2	840	670	300	810
1,5	1050	1050	550	1010
1,6	1120	1300	630	1070
1,8	1260	1650	800	1110
1,9	1330	2030	960	1170
2,0	1400	2100	1000	1300
2,2	1540	2760	1360	1400
2,5	1750	3850	1950	1600
3,0	2100	5200	2700	1800

	Einheit / unit of measurement	Wert / value	Toleranzen / tolerances	Testmethode / testing method
Stärke / caliper	mm		'+/- 5 %	ISO 534
Format / size	Formate / Zuschnitte cm / mm Large sheets / rotary cut pieces cm / mm		'+/- 1,0 mm / '+/- 0,25 mm	
Feuchte / humidity	%	8,0	'+/- 1,5 %	ISO 287

PRÜFKLIMA | TESTING CLIMATE 50% RH, 23°

Smurfit Kappa

Änderungen vorbehalten, Stand 08.2020/
 subject to change, date of issue 2020-08

SOLID BOARD | ANSPRECHPARTNER | CONTACT

Smurfit Kappa Wrexen Paper & Board GmbH
 Orpethaler Str.50 | DE-34474 Diemelstadt
 Tel: + 49 (0) 564 279-0 | Mail: sales.board.wrexen@smurfitkappa.de